

THINK THE FUTURE

Data sheet EQOPOLEN

EQO PO/G



properties	Unit	Figure
Polyethylene content	%	> 65
Humidity	%	~ 0,30
E-Module	Mpa	~ 700
Tensile strenght	Mpa	~ 17
MFI (190/5)	g/10 min	~ 8 (+/-1)
Density	Kg/l	~ 0,960

(These data are expressed as mean values of the month. Therefore, discrepancies can not be excluded.)

Contact:

Herr Stephan Eing

Telefon: 02542/9174-111

E-Mail: stephan.eing@eing.info

Frau Mechthild Ahaus

Telefon: 02542/9174-113

E-Mail: mechthild.ahaus@eing.info

Certified Quality Management System according to *DIN EN ISO 9001:2015* and as a waste management company according to § 56 *KrWG* and the Standard *EuCertPlast*

Hubert Eing Kunststoffverwertung GmbH
Stadtlöhner Straße 71
48712 Gescher
www.eing.info

