

THINK THE FUTURE

Data sheet EQOPOLEN

EQO PP/A



Properties	Unit	Figure
Polypropylen content	%	> 96
Humidity	%	~ 0,30
Grain size	mm	< 10
Bulk weight	kg/l	~ 0,3 – 0,4
MFI (230/2,16)	g/10 min	~ 12,5 (+/-1)
Density	Kg/l	~ 0,915 - 0,925

(These data are expressed as mean values of the month. Therefore, discrepancies can not be excluded.)

Contact:

Herr Stephan Eing

Telefon: 02542/9174-111

E-Mail: stephan.eing@eing.info

Frau Mechthild Ahaus

Telefon: 02542/9174-113

E-Mail: mechthild.ahaus@eing.info

Certified Quality Management System according to *DIN EN ISO 9001:2015* and as a waste management company according to § 56 *KrWG* and the Standard *EuCertPlast*

Hubert Eing Kunststoffverwertung GmbH

Stadtlöhner Straße 71

48712 Gescher

www.eing.info

